



The Eco-Ethical Company

gruppo mauro saviola

GRUPPO MAURO SAVIOLA S.r.l.

Viale Lombardia, 29 I 46019 I Viadana (MN) - Italy I ph: +39 0375 7871 I fax: +39 0375 787300

C.F. e P.IVA 02317900203 REA MN242591 I REG. IMPRESE 02317900203 I Company subject to coordination of its activities by Saviola Holding S.r.l.
Facilities: Viadana - Mortara (PV) - Sustinente (MN) info@gruppomaurosaviola.com I www.gruppomaurosaviola.com

Code: **GR-04**

Rev. **02**

Pag. **1/3**

19/01/2015

PRODUCT DATA SHEET

V 70 Raw Ecological Particleboard Panel

Panel type
P2 (EN 312)

Italian Product



Using recycled wood and a "total green" approach, through an integrated production chain, allow the creation of environmentally friendly products.

Physical-mechanical properties*

GENERAL REQUIREMENTS FOR SHIPMENT

Denomination	Reference standard**	Values
Thickness tolerance	UNI EN 324-1 – UNI EN 14323	± 0,3 mm
Length width	UNI EN 324-1 – UNI EN 14323	± 5 mm
Edge-banding straightness tolerance	UNI EN 324-2	1,5 mm/m
Edge-banding squaring up (orthogonality)	UNI EN 324-2	2 mm/m
Flatness (only on balanced surfaces)	UNI EN 14323	≤ 2 mm/m
Edge-banding damage	UNI EN 14323	≤ 10 mm

PANEL

Denomination	Reference standard**	Values
Mass density	UNI EN 323	Kg/m ³ 670/730
Moisture content	UNI EN 322	9 ± 4 %
Tensile strength - internal bond	UNI EN 319	N/mm ² ≥ 0,35
Surface separation	UNI EN 311	N/mm ² ≥ 0,8
Bending strength	UNI EN 310	N/mm ² 12 ± 4
Screw holding strength - surface	UNI EN 320	N 1.100
Screw holding strength - edge-banding	UNI EN 320	N 850
Heating value	-	Kcal/kg 2.142 - MJ/kg 9
EC reaction class to fire	EN 13501-1 / D.M. 26/6 - 84	D-s2, d0 Dfl-s1 – Class 2
Swelling after 2 hours	UNI EN 317	% ≤ 3
Swelling after 24 hours	UNI EN 317	% ≤ 14
Formaldehyde emissions	UNI EN 120	Class E 1
Formaldehyde release	UNI EN 717-1	ppm ≤ 0,1

* The listed values and classifications should be construed as standards referring to the **18 mm** average thickness.

** The reference standards must be considered in the latest version.

RAW PANEL IS AVAILABLE IN THE FOLLOWING STANDARD SIZES

Sizes	U.M.	Min.	Max.
Thickness	mm	8	40
Length	mm	3.760	5.600
Width	mm	1.860	2.200
Non-standard	mm	On request, subject to acceptance by Gruppo Mauro Saviola Srl	



Italian Product


Code: **GR-04**
Rev. 02 -19/01/2015
Pag. 2/3

Information about the resins used

Acronym	Denomination	Statement
S.V.H.C.	Substance of Very high Concern	There is no presence of any SVHC substance shown in the latest ECHA list.
S.C.C.P.s (C10-C13)	Shorn Chain Chlorinated Paraffins (C10-C13)	There is no presence of Short-chain chloroparaffins (C10-C13)
R.E.A.C.H.	Registration, Evaluation, Authorisation and Restriction of Chemical substances (EC) Regulations No. 1907/2006	Urea resins are a polymer that according to REACH (Title I, Chapter 2, Article 3, Section 5) are exempt from registration .

Certifications

Certifying agency	Denomination
CERTIQUALITY	UNI EN ISO 9001:2008 - Quality system
FSC	Cert. No.: FSC-CQ-COC-000001 - 100% Recycled
CERTIQUALITY	LIG 01/2000 - Certifies the exclusive use of recycled wood in the production of Raw Particleboard Panels
CATAS	CATAS Quality Award Formaldehyde E1
CERTIQUALITY	REMADE in ITALY - Certifies sustainable recycling in Italy





Italian Product

Code: **GR-04**
Rev. 02 -19/01/2015
Pag. 3/3

FSC® Product

Description	Product type	Production sites	Species	Main output category	Control System	Main input category
Raw Particleboard Panel	W8.2 Particleboard	Mortara, Sustinente, Viadana	Not known	FSC®-recycled	Trasfer system	Reclaimed material (post-consumer)

ALL THE SUPPLIES OF V 70 RAW ECOLOGICAL PARTICLEBOARD PANELS FROM GRUPPO MAURO SAVIOLA srl ARE PROVIDED WITH A DECLARATION OF EC CONFORMITY, IN COMPLIANCE WITH THE DECREE 10 October 2008 (OJ No. 288 10/12/08)




Certificate n°:	55 / 2004	Spett.:	GRUPPO MAURO SAVIOLA SRL-STABILIMENTO DI MORTARA VIALI DAVINCI S.P.A. BOX 89 27035 MORTARA (PV) ITALIA c.a. Ing. Gilberto Bonesi
Internal protocol n°:	92		
Report n°:	2813		
Emission date:	31/10/14		
Award certificate expiry date:	31/05/15		
Certification:	CDQ Formaledehyde E1		
Certified product name:	Pannelli di particelle grigio unico, idrofugo, ignifugo, EPF-S		

First audit report for year 2014

1 - Internal control

Nr. requested internal controls from January to June: **20**
Nr. received internal controls from January to June: **48**

The controls carried out according to the prescriptions described by the EN 12092 standard in the period from January to June 2014 have shown an average value of **6.25** mgHCHO/100g and a 95th percentile of **7.57** mgHCHO/100g. Both values are below the limits established for E1 class panels (average value below 6.50 mgHCHO/100g and 95th percentile below 8.00 mgHCHO/100g). The following histogram shows the data distribution obtained.



pag. 1

The V 70 Raw Ecological Particleboard Panel is a product that does not fall under the European regulations REACH (Reg. EU 1907/2006) and CLP (Reg. EU 1272/2008).

Therefore the preparation of a Safety Data Sheet is NOT required.